

ABSTRACT

A<sup>2</sup> In a process to reduce the susceptibility to ~~scabbing~~<sup>dross-forming</sup> of an aluminium alloy melt with a content of at least 2.5 w.% magnesium, to the melt is added 0.02 to 0.15 w.% vanadium and less than 60 ppm beryllium. By the addition of vanadium, the beryllium addition can be reduced and at the same time the ~~scabbing~~<sup>dross-forming</sup> resistance of the melt increased.

09710900-121800